

THERMAL PERFORMANCE - GLAZING SELECTION CHART








Contact CRL-U.S. Aluminum Technical Sales at (800) 262-5151 in the U.S. or Canada, or (323) 588-1281 (International). Ask for Extension 15305. Additional product details are available online at crlaurence.com/window-walls.



BT525 Window Wall SSG

Below are various insulating glazing assemblies and spacer combinations that will provide this system with U-factors ranging from a low of 0.19 to a high of 0.53. If your particular combination of glazing and spacer isn't shown, please contact a CRL - U.S. Aluminum Technical Sales Representative and initiate a request. One of our on-staff thermal simulation engineers will conduct the calculations and return a report that can be utilized for bidding and design purposes.

TYPICAL DETAILS:



GLAZING ASSEMBLY - 1" INSULATED	CENTER OF GLAZING U-FACTOR ⁵	CENTER OF GLAZING SHGC ⁶	CENTER OF GLAZING VT ⁶	SPACER	OVERALL SYSTEM U-FACTOR ⁵	OVERALL SYSTEM SHGC ⁶	OVERALL SYSTEM VT ⁶
1/4" SunGuard SNX 62/27 Clear1 / 1/4" Xenon / Heat Mirror 77 Film / 1/4" Xenon / 1/4" SunGuard IS 20 Clear3	0.09	0.20	0.48	Super Spacer	0.19	0.18	0.41
1/4" SunGuard SNX 62/27 Clear1 / 1/2" Xenon / 1/4" SunGuard IS 20 Clear4	0.18	0.25	0.60	Stainless	0.28	0.23	0.52
1/4" Solarban 70XL Starphire1 / 1/2" Argon / 1/4" Clear	0.24	0.27	0.64	Stainless	0.33	0.25	0.56
1/4" Solarban 60 Clear1 / 1/2" Argon / 1/4" Clear	0.24	0.38	0.70	Aluminum	0.35	0.35	0.62
1/4" Cardinal 272 Clear1 / 1/2" Argon / 1/4" Clear	0.25	0.40	0.70	Aluminum	0.35	0.36	0.61
1/4" Solarbronze / 1/2" Air / 1/4" Solarban 60 Clear2	0.29	0.31	0.42	Aluminum	0.39	0.29	0.37
1/4" Clear / 1/2" Air / 1/4" Solarban 70XL Starphire2	0.29	0.37	0.64	Aluminum	0.38	0.33	0.56
1/4" Solarban 60 Clear1 / 1/2" Air / 1/4" Clear	0.29	0.38	0.70	Aluminum	0.39	0.35	0.62
1/4" Cardinal 272 Clear1 / 1/2" Air / 1/4" Clear	0.29	0.40	0.70	Aluminum	0.39	0.36	0.61
1/4" Clear / 1/2" Air / 1/4" Clear	0.47	0.70	0.79	Aluminum	0.53	0.65	0.70

1. Low-e on #2 surface 2. Low-e on #3 surface 3. Low-e on #6 surface 4. Low-e on #4 surface 5. In accordance with NFRC 100 6. In accordance with NFRC 200

Solarban is a registered trademark of Vitro Architectural Glass. SunGuard is a registered trademark of Guardian Industries Corp.