C.R. Laurence products are trusted and respected throughout the industry. Whether you are selling pre-cut rolls to the consumer, repairing screens in your shop, or selling rolls of screening to contractors or the housing industry, we've got you covered.

We are the only insect screening source to also provide a full line of screen accessory items. Our screening products include aluminum, fiberglass, pool and patio screen, solar screen, no-see-um screen, bronze, galvanized steel, and vent mesh.

## **PROPERTIES**

- Very durable and pet resistant
- Polyester has greater tear strength, durability, and will last three times longer than fiberglass mesh
- Easy to Install



## **TECHNICAL CHARACTERISTICS**

| PROPERTY               | TEST METHOD | RESULTS         |
|------------------------|-------------|-----------------|
| Mesh (ends/inch)       | ASTM D 3775 |                 |
| a) Warp                |             | 17.00 – 18.25   |
| b) Fill                |             | 17.00 – 18.25   |
|                        |             |                 |
| Coated Diameter (in.)  | ASTM B 557  | .007 – .009     |
| T 11 01 11             | 40TM D 557  | 0.401 : 0.001 : |
| Tensile Strength       | ASTM B 557  | 210ksi – 280ksi |
| % Elongation           | ASTM B 557  | 1% – 10%        |
|                        |             |                 |
| Stiffness (mg)         | ASTM D 3656 |                 |
| a) Warp                |             | 1200 – 2600     |
| b) Fill                |             | 1200 – 2600     |
| Mesh Weight (oz/yd sq) | ASTM D 3776 | 7.0 – 8.0       |
|                        |             |                 |
| Openness (%)           | TMS-TM-009  | 68 – 74         |
|                        |             |                 |
| Fabric Thickness (in.) | ASTM D 1777 | .014 – .018     |



All statements herein are expressions of opinion, which we believe to be accurate and reliable, but are presented without guarantee or responsibility on our part. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended. Values presented above are nominal and only to be used as guidelines.

