

C.R. Laurence Co., Inc.
2503 E. Vernon Ave.
Los Angeles, CA 90058-1826
(800) 421-6144

CRL Cat. No: PSB040 , PSB080 , PSB125, PSB156, PSB375, and PSB250

APPLICATIONS:

NB802-85A PVC compound are applicable for soft and rigid co-extrusion profiles, mainly used in supermarket shelf labels, water bar on the glass shower door and other co-extrusion products connected by this soft pvc compound

FEATURES:

- Good extrusion processing performance;
- The same processing temperature with the host products;
- Excellent fusion, weather resistance, resistance to tear;
- Meet the requirements on REACH.

PROPERTIES:

Item	Test standard	Typical value	Item	Test standard	Typical value
(g/cm ³) Specific Density	ASTM D792	1.23~1.28	Transmittance rate	ASTM D1003 MethodA (0.75mm)	≥92%
psi Tensile Strength	ASTM D638	≥15MPa	Haze degree	ASTM D1003 MethodA (0.75mm)	≤2%
Elongation at Break	ASTM D638-03 (50mm/min)	≥110%	Shore A(Hardness)	ASTM D2240	82~88

Processing temperature range: 168°C~185°C

Product packaging: Packed in 25Kg paper bags;

Special note: This product description of relevant data, in particular test is given under the conditions of the relevant data, customer products should be recognized in accordance with their own use and environmental requirements to be identified and verified. We provide only the relevant technical data Customers to use the process of reference.

**FICHE TECHNIQUE
TECHNICAL DATA**

Composé Compound	RX 12285 JA CLEAR
Grade Grade	Extrusion
Densité spécifique Specific gravity	1.24 gr/cc
Elongation	300%
Résistance à la tension Tensile strength	2550 psi
Point de rupture Brittleness point	-26 C°
Dureté (15 sec.) Hardness (15 sec.)	85 shore A
Application	General Purpose phtalate-free

**Ce composé contient un fongicide pour prévenir la dégradation du produit dû aux microorganismes. Ce fongicide ne protège pas l'utilisateur contre les bactéries, virus, germes ou autres maladies.

**This compound contains an antimicrobial agent to prevent microorganisms from degrading the product. This antimicrobial does not protect users or others against bacteria, viruses, or other disease organisms.

Les renseignements et recommandations fournis ici sont, autant que nous sachions, précis et sûrs. Ils sont cependant publiés sans garantie d'exactitude. Tout produit est vendu à la condition que l'acheteur s'assure par ses propres essais que le produit correspond à ses besoins particuliers. En outre, l'acheteur assume tout risque et toute responsabilité émanant de l'utilisation dudit produit, même si cette utilisation est conforme aux instructions du vendeur. Ces informations n'impliquent ou n'octroient aucun droit ou permission d'utilisation qui pourrait violer des brevets, lois, codes de sécurité ou règles d'assurance. Le présent document ne comporte pas de garantie de commercialisation ou autre.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. This information does not imply or otherwise convey any rights or permission for use which will violate any patent rights, laws, safety codes or insurance regulations. There is no warranty of merchantability and there are no other warranties for the products described.