

DOWSIL™ Silicone Glazing Sealant

FEATURES & BENEFITS

Professional quality sealant specifically formulated to meet glass shop glazing needs

- Cures to 100% silicone rubber
- Resistant to sunlight and weather extremes
- High strength, excellent adhesion
- Remains flexible, will not become brittle, crack, shrink or chalk
- Bonds to many common substrates
- Supplied in removable, reusable, resealable nozzle that saves time and sealant

COMPOSITION

One-part, acetoxy-cure, RTV silicone

APPLICATIONS

- General glazing applications, backlite replacement and skylight installations
- Repairing weatherstripping and gaskets
- Sealing most glass, plastics, metal, repainted surfaces, fiberglass, ceramics and aluminum substrates

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Unit	Result
Tooling Time ¹	minutes	< 10
Tack-Free Time ¹	minutes	10–15
Complete Set-Up Time ¹ , 1/8"	hours	24
Cure System		Acetoxy
Application Temperature Range	°F (°C)	-20 to 122 (-29 to 50)
VOC Content ²	g/L	22
As Cured – After 7 days		
Durometer Hardness Shore A	points	26
Tensile Strength	psi	251
Elongation	percent	470
Temperature Range (Continuous)	°F (°C)	-40 to 350 (-40 to 176)
Movement Capability	percent	±25

1. At 25°C (77°F) and 50% relative humidity.

2. Based on South Coast Air Quality Management District of California. Maximum VOC is listed both inclusive and exclusive of water and exempt compounds.

crlaurence.com



DOWSIL™ Silicone Glazing Sealant

DESCRIPTION

DOWSIL™ Silicone Glazing Sealant is a professional quality sealant specifically formulated to meet glass shop glazing needs. It forms a long-lasting, water-resistant seal with $\pm 25\%$ movement capability when properly applied. Its unique adhesion-promoted formulation ensures adhesion to many building substrates, and longer working time means a professional appearance for the finished job.

DOWSIL Silicone Glazing Sealant meets the requirements of:

- ASTM C920 Type S, Grade NS, Class 25, Use NT, G and A
- TT-S-001543A
- TT-S-00230C, Class A (COM-NBS)

HOW TO USE

1. Refer to product packaging for use-by date.
2. Temperature. Apply sealant at temperatures between -20 and 122°F (-29 and 50°C) for best results.
3. Prepare Surface. Cut out and remove all old caulk for repair applications.
4. Clean, Two-Step. First, apply solvent to a lint-free cloth and vigorously wipe bonding surfaces to remove dirt and residues. Next, use a dry wipe to remove remaining solvent and residue for optimum cleaning. Repeat if necessary. Surfaces must be clean, dry, oil- and frost-free for best results. (Recommended solvents include isopropyl alcohol, toluene, xylene, naphtha or similar solvent.) Always wear gloves and follow safety precautions and directions on solvent container. DO NOT USE gasoline or kerosene.
5. Install. Install back-up spacing material for better filling, especially if width exceeds $1/2"$ to maximize bonding results. Open-cell polyethylene foam backer rod can be used.
6. Mask. Apply masking tape to areas adjacent to the joint to ensure straight bead lines and easy cleanup. Remove masking tape immediately after the bead is completed and before a skin forms.
7. Open Cartridge. Cut snub nose above threads, reattach and cut nozzle to desired size. Insert into a caulking gun.
8. Apply. Extrude sealant with a smooth, steady motion, and ensure complete fill of joint cavity before proceeding.
9. Tool. Tool the sealant immediately after application and before a skin forms. Remove masking immediately after tooling.
10. Replace Cartridge Cap. See "Usable Life and Storage" instructions.

CLEANUP INSTRUCTIONS

1. Cleanup should start immediately after sealant has been applied/ tooled and masking tape removed.
2. While wearing solvent-resistant gloves, wipe off excess sealant from surfaces and tools with a solvent-moistened cloth within 10 minutes of application.
3. If excess sealant is completely cured, carefully cut or scrape away.
4. Avoid contact of uncured sealant with skin and clothing. If contact does occur, wipe with clean rags and wash with water.

crlaurence.com

DOWSIL™ Silicone Glazing Sealant

HANDLING PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS ON OUR WEBSITE WWW.CRLAURENCE.COM.

USABLE LIFE AND STORAGE

Product should be stored at or below 32°C (90°F) in original, unopened containers.

LIMITATIONS

- Not for structural glazing
- Not paintable
- Not suited for prolonged submersion in water or below-grade applications
- May not adhere to oily woods or be compatible with substrates made of methylmethacrylate, polycarbonate, polypropylene, polyethylene, and polytetrafluoroethylene
- Not suitable for surfaces that might bleed oils, plasticizers or solvents, or porous surfaces such as cementlike materials, stone or surfaces prone to attack by weak acids
- May not cure properly if used in spaces confined from atmospheric moisture
- May cause corrosion on some brass, copper, zinc or zinc alloy-containing fixtures

- Not for use where abrasion and physical abuse are encountered
- This product is neither tested nor represented as suitable for medical or pharmaceutical uses

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

CRL's sole warranty is that our products will meet the sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

CRL DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

crlaurence.com